

Our Ref: SW/SW

4 December 2024

**Report 428785/6**
**Page: 1 of 3**

Camira Fabrics Limited  
Meltham Mills  
Meltham  
United Kingdom  
West Yorkshire  
HD9 4AY

Contact: Luke Russell;Amanda Jack

DATE RECEIVED : 13 NOV 2024  
QUALITY/REFERENCE : HALCYON CEDAR  
REPUTED FIBRE CONTENT : NOT GIVEN  
FABRIC DESCRIPTION : WOVEN  
COLOUR/DESIGN : NUTMEG  
STYLE NUMBER : C17979  
ORDER NUMBER : 83A30149

PERFORMANCE STANDARD : GENERAL

TEST PERFORMANCE DATE(S) : 04/12/2024


**REPORT SUMMARY**

Tests	Method	Pass	Fail	Requirement
Hydrostatic head	Hydrostatic Head BS 3424-26:1990 Method 29A			No requirement

Eurofins MTS Consumer Product Testing UK Ltd  
118 Lupton Avenue, Leeds, West Yorkshire, LS9 6ED  
Tel: 0113 248 8830 Email: info@hstts.co.uk  
Registered No. 7337435 VAT No. 887127683

4 December 2024

**Report 428785/6****Page: 2 of 3****S. WISEMAN**  
**LABORATORY DIRECTOR**

*This report may not be reproduced except in full without the written approval of Eurofins MTS Consumer Product Testing Services Limited. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.*

Eurofins MTS Consumer Product Testing UK Ltd  
118 Lupton Avenue, Leeds, West Yorkshire, LS9 6ED  
Tel: 0113 248 8830 Email: [info@hstts.co.uk](mailto:info@hstts.co.uk)  
Registered No. 7337435 VAT No. 887127683

4 December 2024

**Report 428785/6****Page: 3 of 3****PHYSICAL****Hydrostatic Head BS 3424-26:1990 Method 29A**

Sample area	100cm <sup>2</sup>
Test atmosphere	20°C ± 2°C 65% R.H ± 4%
Water temperature	20°C
Rate of rise of water pressure	60cm/min

Test 1	178 cm/H <sub>2</sub> O
Test 2	146 cm/H <sub>2</sub> O
Test 3	136 cm/H <sub>2</sub> O
Test 4	126 cm/H <sub>2</sub> O
Test 5	141 cm/H <sub>2</sub> O

Mean	145 cm/H <sub>2</sub> O
------	-------------------------

NB - Backing material delaminated and burst during test on all samples

Requirement: No requirement