



LANCASHIRE TESTING SERVICES LIMITED

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

www.ltslab.co.uk



9630

TEST CERTIFICATE

CLIENT:	Camira Fabrics Meltham Mills, Meltham Huddersfield HD9 4AY - - -	Certificate Number:	UK2101351 -2
		Date Received:	10/12/2021
		Date Issued:	20/04/2022
		Issue Number:	2
		Changes made from previous issue (if applicable)	
Contact:	Rebecca Grimes	Sample name changed from Main Line	
Tel:	01924 481366	Flax/ Main Line Stripe	
Email:	rebecca.grimes@camirafabrics.com		

SAMPLE IDENTIFICATION	
The information in this section is provided by the client and Lancashire Testing Services Ltd assumes no responsibility or liability for its accuracy.	
Sample Name / Reference	Main Line Flax/ Twist
Additional Names:	-
Batch Ref/Number:	-
Order Number:	-
Colour:	-
Fabric Composition:	-
Customer:	-

SPECIFICATION	
BS5867-2:2008 Fabrics for curtains, drapes and window blinds	
Type B	
TEST METHOD	
Flammability:	BS EN ISO 15025:2002 - Procedure A -Surface Ignition
Pre-treatment:	BS EN ISO 10528:1995:12 Commercial wash cycles at 75°C
	-

Conclusion	
The sample tested:	Complies with the flammability requirements of:
BS5867-2:2008 Type B	As supplied & after cleansing procedures as described above
Taking into account uncertainty of measurement	
Measurements of uncertainty: Time ±1 second, Dimension ±1mm	

This report relates only to the sample tested and does not guarantee the bulk of the material to be of equal quality

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

www.ltslab.co.uk



9630

TEST CERTIFICATE**Test Results:-****BS5867-2:2008 Fabrics for curtains, drapes and window blinds****Type B**

"The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use."

Sample Code	UK2101351 -2					
Sample Name / Reference	Main Line Flax/ Twist					
Client	Camira Fabrics					
Date of test	20/12/2021					
Pre-Treatment	BS EN ISO 10528:1995:12 Commercial wash cycles at 75°C Tumble Dried in accordance with BS EN 26330:1994					
Test Conditions	Period h	Temperature °C		Relative humidity %	Air Flow m/s	Volume m ³
Conditioning of test specimens	≥24	20±2		65±5	-	-
Testing conditions	-	10-30		15-80	≤0.2	≥4
Flame Application time	15 second Face burn			Flame Height (vertical)		40 ± 2mm
Sample size	200 x 160mm			Fabric face tested		Outer
Longest Dimension	Machine Direction			Cross Direction		
As Supplied	1↑	2↓	3↑	4→	5←	6→
Duration of Afterflame (s)	0	0	0	0	0	0
Duration of Afterglow (s)	0	0	0	0	0	0
Flame reached an edge	NO	NO	NO	NO	NO	NO
Hole reached an edge	NO	NO	NO	NO	NO	NO
Flaming Debris	NO	NO	NO	NO	NO	NO
Damage length Horizontal (mm)	28	29	28	29	29	28
Damage length Vertical (mm)	72	76	76	79	74	72
RESULT:	PASS					

After Wash Procedures	1↑	2↓	3↑	4→	5←	6→
Flame reached an edge	0	0	0	0	0	0
Hole reached an edge	0	0	0	0	0	0
Flame reached an edge	NO	NO	NO	NO	NO	NO
Hole reached an edge	NO	NO	NO	NO	NO	NO
Flaming Debris	NO	NO	NO	NO	NO	NO
Damage length Horizontal (mm)	28	30	30	29	29	28
Damage length Vertical (mm)	62	67	65	67	64	63
RESULT:	PASS					
Deviation from specified procedure:	-					

Please note that copies of this original certificate are not valid

Issue Number: 2

This report relates only to the sample tested and does not guarantee the bulk of the material to be of equal quality



LANCASHIRE TESTING SERVICES LIMITED

Lyon Road Industrial Estate : Kearsley : Bolton
Lancashire : BL4 8NB
Tel: +44 (0) 1204 792858
Email: enquiries@ltslab.co.uk
www.ltslab.co.uk



9630

Craig Allardice Laboratory Technician	Tony Alcock Laboratory Technician	John Marsh Laboratory Supervisor	Peter Collings Operations Manager

Decision Rule:
 Lancashire Testing Services have measurement uncertainties for all test standards (available on request) and have applied these measurements to the test result.
 The specific level of risk is < 2.5% as stated in ILAC-G8:09/2019. Unless otherwise indicated L.T.S will apply this rule to all measurements reported.

If the measurement result plus/minus the expanded uncertainty with a 95 % coverage probability overlaps the limit, it is not possible to state compliance or non-compliance. The measurement result and the expanded uncertainty with a 95 % coverage probability will then be reported. The report will include the actual value with the uncertainty range.

Lancashire Testing Services Ltd have conducted thorough analysis of the uncertainty of all measurements carried out in the application of the standard or standards detailed in this report. Where possible any associated uncertainty of measurements have been accounted for in the working instructions, so that they have no impact on the reporting of the final result. In instances where uncertainty of measurements can only be taken into account after the test has been conducted, these uncertainty values have been stated on this report. The stated uncertainty of measurement has also been taken into account in the final reporting of the overall result.

Information provided about a customer, from a source other than the customer, shall only be shared with the customer. The provider of the information shall remain confidential to the laboratory unless agreed by the source of the information.

Please note that copies of this original certificate are not valid

Issue Number: 2

This report relates only to the sample tested and does not guarantee the bulk of the material to be of equal quality