

**Client:** Camira Fabrics Ltd  
Meltham Mills  
Meltham  
West Yorkshire  
HD9 4AY

**Entry No:** 68124-01

**Date received:** 16/12/2014

**Client's Description:** Sample of fabric: Aspect, Call 2934

## TEST REPORT

**Test Required:** Abrasion

**Conditioning:** In accordance with BS EN ISO 139:2005 for a minimum of 24 hours at 65+/-4% Relative humidity , 20+/-2°C.

**Method of Test:** BS EN ISO 12947-2:1998

**Date of Test:** 7.1.15 to 12.1.15

The tests were carried out using a pressure 12+/-0.3kPa.  
The criterion for judging end point was two threads broken.

Specimen 1	55,000 rubs to 60,000 rubs
Specimen 2	55,000 rubs to 60,000 rubs
Specimen 3	50,000 rubs to 55,000 rubs
Specimen 4	45,000 rubs to 50,000 rubs
Mean	50,000 rubs to 55,000 rubs

Change in colour after 3,000 rubs 4-5

Observation Technique: - 10 Fold Magnification  
Type of Fabric: - Flat Woven

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein.*

*V Brockbank*

V Brockbank  
Senior Technician  
Date of original 14<sup>th</sup> January 2015  
Date of amendment 11<sup>th</sup> May 2016



- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

