



## TEST REPORT

**Client:** Camira Transport Fabrics Limited  
The Watermill  
Wheatley Park  
Meltham  
WF14 8EH

**Entry No:** 84268

**Date received:** 12/05/2017

**Client's Description:** Sample of fabric: 745/754/750/765/SK33/SK30 wool rich moquette, wire woven - cut/cut and loop, Colour: BEM582

**Test Required:** Flammability

**Conditioning:** A minimum of 24 hours at 50+/-5% Relative Humidity, 21+/-1°C

**Date Tests Completed:** 22/05/2017

**Method of Test:** FMVSS 302

### Results:

On all five specimens flaming did not reach the first marker.

### Comments

On the basis of the tests carried out this sample meets the requirements of FMVSS 302.

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein*

Dale Brockbank  
Materials Testing Manager  
22 May 2017

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
  - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
  - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104