

TEST REPORT

Report Ref.	LEI25090076A Supplemented		
Date Received	01/09/2025	Date Issued	18/09/2025

Company Name & Address	Camira Fabrics Limited The Watermill Mirfield, WF14 8HE GBR
Contact Name	Amanda Jack

Order Number	83A34017
Ref / Style Number	568750
Colour	Aubergine D1644D
Quality	Upland
End Use	Upholstery
No Of Samples	1
Retailer	General

Test	Method	Sample	Result
Martindale Abrasion Resistance	BS EN ISO 12947-2: 2016		See Results

Tests marked (^) in this report have been performed by an approved 3rd party laboratory.
Tests marked (*) in this report are not included in our UKAS scope of accreditation.



Lauren Roberts
(Technician)

Martindale Abrasion Resistance BS EN ISO 12947-2: 2016

Conditioning Parameters: 20°C±2°C & 65% rH±4% rH

	Results	Requirement
Shade change @ 6000	4-5	
	Abrasion Resistance*	
Specimen 1	63000 Revs	
Specimen 2	69000 Revs	
Specimen 3	66000 Revs	
Overall result**	63000 Revs	
Test Information		
Test load:	12 kPa	
Fabric type	Woven	
Breakdown criteria	Two threads completely broken	
Inspection interval	Every 10,000 Revs	
Foam used	Yes	
Preparatory treatment	No	
*The abrasion resistance result is the last inspection point at which no breakdown was observed.		
**The overall result is the lowest individual test result of all the test specimens tested.		

Overall Test Result: See Results

Uncertainty: ±17.1%

Report Type	Issue Date	Revision Reason	Revision Description
Original	09-Sep-25	Complete Original Issue	N/A
Supplemented	18-Sep-25	Other Correction	Abrasion result correction

The client acknowledges and agrees that any services provided and/or reports produced by Intertek are done so within the limits of the scope of work agreed pursuant to the client's specific instructions. This report relates specifically to the sample(s) tested that were drawn and delivered by the client or their nominated third party. Intertek does not make any representation or warranty for any bulk samples or certify the bulk samples received from the client. Furthermore, Intertek does not provide a warranty or verification on the sample(s) representing any specific goods, material and/or shipment and only relate to the sample(s) as received and tested. Intertek have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct. In no event, will the contents of any reports or any extracts, excerpts or parts of any reports be distributed or published without the prior written consent of Intertek in each instance. Only the client is authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor of $k = 2$, providing a level of confidence of approximately 95 %. Unless otherwise specified all compliance and pass/fail statements are binary simple acceptance based on the tolerance interval and, with the exception of graded methods, a test uncertainty ratio greater (TUR) than 4:1. For graded methods the TUR will drop to as low as 0.5:1 when the tolerance limits are within a grade division of the upper scale limit. The Uncertainty budgets are stated for each Test method, these are for reference and where a % value is stated it should be applied to the stated result, this % value is accurate at the acceptance limit, where results are significantly different to the acceptance limit the calculated uncertainty may be over or understated. Uncertainty should be carefully considered when results are on or close to Specification Limits / Requirements - in such cases it should be noted that the risk of false acceptance or rejection may be as high as 50%, for further information please refer to ILAC G8.