



Confidential Report

Our Ref: 27/06448/04/24





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 17 May 2024

Our Ref: 27/06448/04/24
Your Ref: 83A26887

Page: 1 of 8

Client: Camira Fabrics Ltd

The Watermill
Wheatley Park
Mirfield
West Yorkshire
WF14 8HE

Job Title: Fire test on one sample of fabric

Clients Order Ref: 83A26887

Date of Receipt: 18 April 2024

Description of Sample: One sample of fabric, referenced; Blazer Lite.
Colour: Wish
Batch: 542807

Work Requested: We were asked to make the following test(s):

BS 476 Part 7
BS 476 Part 6

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited

Note: This report relates only to the items tested.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 17 May 2024

Our Ref: 27/06448/04/24
Your Ref: 83A26887

Page: 2 of 8

Client: Camira Fabrics Ltd

FIRE TESTS ACCORDING TO BS 476:PART 7:1997 (Method for classification of the surface spread of flame of products)

Date of Test: 13/05/2024

Conditioning

The sample was conditioned to constant mass at a temperature of $23\pm 2^{\circ}\text{C}$ and a relative humidity of $50\pm 10\%$ and maintained in this condition until required for testing

Mounting Method

Each specimen was tested fully adhered to a 12mm calcium silicate board, using PVA adhesive.

Procedure

The test was carried out in accordance with BS 476:Part 7: 1997. The sponsor sampled the material and the panels were cut from the sample to the dimensions set out in the standard by the sponsor.

The following were recorded:-

- the time at which the flame front crosses each vertical reference line;
- the maximum extent of flame spread during the first 1.5 min from the start of the test;
- the maximum extent of flame spread during the whole test i.e. 10 min or less (if applicable)
- the time (and distance) at which maximum flame spread is reached.

The flame spread at 1.5min and the final flame spread results were compared with the standard class limits and a classification was assigned.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
 Telephone: +44 (0) 113 259 1999
 Email: onestopshop@bttg.co.uk
 Website: www.bttg.co.uk

Date: 17 May 2024

Our Ref: 27/06448/04/24
 Your Ref: 83A26887

Page: 3 of 8

Client: **Camira Fabrics Ltd**

Requirements

The class limits for flamespread, detailed in BS 476:Part 7: are set out below.

	Flame spread at 1.5 min (mm)	Final flame spread (mm)
Class 1	165 (+25)	165 (+25)
Class 2	215 (+25)	455 (+45)
Class 3	265 (+25)	710 (+75)
Class 4	Exceeding Class 3 limits.	

A definitive classification is based on a sample of six specimens and the figure in brackets gives the tolerance by which only one specimen in six may exceed the class limit assigned.

Results

The test results relate only to the behaviour of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Time for flame spread to reach (s)								Flame spread at 1.5 min (mm)	Maximum flame spread (mm)	Time to reach maximum flame spread (s)
75	165	215	265	455	710	785	825			
--	--	--	--	--	--	--	--	70	70	60
--	--	--	--	--	--	--	--	70	70	60
--	--	--	--	--	--	--	--	65	65	60
--	--	--	--	--	--	--	--	65	65	60
--	--	--	--	--	--	--	--	65	65	60
--	--	--	--	--	--	--	--	70	70	60

BS 476:Part 7 Classification

The results indicate that the sample met the performance requirements of Class 1.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
 A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
 BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
 The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
 Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 17 May 2024

Our Ref: 27/06448/04/24
Your Ref: 83A26887

Page: 4 of 8

Client: Camira Fabrics Ltd

FIRE TESTS ACCORDING TO BS 476-6:1989+A1:2009 (2020)

Fire tests on building materials and structures. Method of test for fire propagation for products

Date of Test: 13/05/2024

Test Method

The test was carried out in accordance with BS 476-6:1989+A1:2009 (2020).

Prior to testing the sample the calibration of the equipment was determined to ensure compliance with the test limits set out in the standard.

The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard by the sponsor.

Temperatures of the flue gases were measured to the nearest degree centigrade at the time intervals and periods set out below, taking zero time as the moment of ignition of the gas supply. The temperature was measured by means of two thermocouples with their measuring junctions located in the cowl of the apparatus as required by the standard.

The relevant temperature-time intervals were observed for each individual specimen and the calibration board according to the ranges 0 to 3 minutes every 30 seconds, 4 to 10 minutes every 1 minute and 12 to 20 minutes every 2 minutes to give 3 time periods.

N.B: The shrinkage in the plane of the calibration board was not determined after heat soaking at 1000°C.

Mounting Method

Each specimen was tested fully adhered to a 12mm calcium silicate board, using PVA adhesive.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 17 May 2024

Our Ref: 27/06448/04/24
Your Ref: 83A26887

Page: 5 of 8

Client: Camira Fabrics Ltd

Calculation of Results

At each time interval the temperature of the calibration board was subtracted from that of the individual specimen temperature, this was then divided by ten multiplied by the time interval.

The sum of each individual value in each time period was then calculated to give an index of performance, s , for each specimen.

The fire propagation index of the product is calculated from the average of the individual s values for the total number of specimens in each time period.

$$\text{Total } I = i_1 + i_2 + i_3$$

A definitive classification is based on a sample of at least three specimens.

Requirements

A Class 0 is the highest National product performance classification for lining materials. To meet Class 0 a material has to meet the requirements laid down in the UK Building Regulations 2010, Approved Document B, Appendix A:2006 Edition (Now withdrawn) that states that a composite material is either:

- composed throughout of materials of limited combustibility; or
- a class 1 material which has a propagation index (I) of not more than 12 and a sub index (i_1) of not more than 6 when tested to BS 476 Part 6.

Results

Number of specimens tested	Sub-index i_1	Sub-index i_2	Sub-index i_3	Total Fire propagation index I
3	5.0	3.3	0.6	8.8



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 17 May 2024

Our Ref: 27/06448/04/24
Your Ref: 83A26887

Page: 6 of 8

Client: Camira Fabrics Ltd

Note

The test results relate only to the behaviour of the test specimen of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use. No guarantee can be given as to the outcome of definitive testing.


It should be noted that to meet the BS 476 Part 6 requirements the above material has also to meet Class 1 at BS 476 Part 7.


Overall Classification

There is no longer an official definition of Class 0, this was specified in the 2006 Edition of Approved Document B which has been withdrawn and superseded by the 2019 Edition. **The results meet the criteria of Class 0**, as specified in Approved Document B, Appendix A, 2006 Edition (Now withdrawn).

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (<https://www.bttg.co.uk/about-us/decision-rules-policy/>) for further information.

Reported by:  A Shute, Section Leader

Countersigned by:  P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 17 May 2024

Our Ref: 27/06448/04/24
Your Ref: 83A26887

Page: 7 of 8

Client: Camira Fabrics Ltd

Uncertainty Budget

The overall uncertainty budgets for BS 476-7:1997 and BS 476-6:1989+A1:2009 (2015) are as follows:-

BS 476-7:1997

Overall: $\pm 12\%$

BS 476-6:1989+A1:2009 (2015)

Overall: $\pm 6\%$



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.