
FLAMMABILITY TEST CERTIFICATE - 79954

COMPANY DETAILS: CAMIRA FABRICS
THE WATERMILL, WHEATLEY PARK, MIRFEILD
WEST YORKSHIRE, WF14 8HE

CONTACT NAME(S): LUKE RUSSELL
TEL: 0192 481368
EMAIL: luke.russell@camirafabrics.com

DATE RECEIVED: 17/01/2020
DATE TESTED: 24/01/2020
DATE ISSUED: 24/01/2020
PO NUMBER: 83A07323

SAMPLE DESCRIPTION: LUCIA CS
COLOUR: COSTA
QUALITY/BATCH REF: 434535
COMPOSITION: NOT STATED
MODEL NO: NOT STATED
SAMPLE END USE: UPHOLSTERY& PANELS
MANUFACTURER: CAMIRA FABRICS
SUPPLIER/BUYER: NOT STATED

PERFORMANCE REQUIRMENT:

BS 5867-2: 2008 Type B – Flammability requirements specification – Fabrics for curtains, drapes and window blinds.

TEST METHOD:

BS EN ISO 15025: 2002 Procedure A (Surface Ignition) – Protective clothing – Protection against heat and flame.
Methods of test for limited flame spread.

PRE-TREATMENT:

One set of specimens had been subjected to the water soak procedure in accordance with Annex D of BS EN 1021-1: 2006, then line dried in ambient atmospheric conditions.

CONDITIONING:

The sample was conditioned for at least 24 hrs in a specified atmosphere at $20 \pm 2^{\circ}\text{C}$ and $65 \pm 5\% \text{ r h}$.

Authorised By:



Zeb Alam
Operations Director

Mark Jones
Quality Manager

Karen Brooks
Managing Director

FLAMMABILITY TEST CERTIFICATE - 79954

TEST RESULTS:

BEFORE CLEANISNG:

Test Criteria	1	2	3	4	5	6
Specimen Direction:	↑	↓	↑	←	→	←
Application Time:	15	15	15	15	15	15
Hole formed: (Y/N)	YES	YES	YES	YES	YES	YES
Hole reached the edge: (Y/N)	NO	NO	NO	NO	NO	NO
Flame reached the edge: (Y/N)	NO	NO	NO	NO	NO	NO
Flaming Debris: (Y/N)	NO	NO	NO	NO	NO	NO
Damage Length: (mm)	48	45	46	49	51	57
Damage width: (mm)	22	21	20	27	24	22
Test Result	PASS	PASS	PASS	PASS	PASS	PASS

AFTER CLEANISNG:

Test Criteria	1	2	3	4	5	6
Specimen Direction:	↑	↓	↑	←	→	←
Application Time:	15	15	15	15	15	15
Hole formed: (Y/N)	YES	YES	YES	YES	YES	YES
Hole reached the edge: (Y/N)	NO	NO	NO	NO	NO	NO
Flame reached the edge: (Y/N)	NO	NO	NO	NO	NO	NO
Flaming Debris: (Y/N)	NO	NO	NO	NO	NO	NO
Damage Length: (mm)	51	53	54	54	52	51
Damage width: (mm)	22	22	22	20	26	23
Test Result	PASS	PASS	PASS	PASS	PASS	PASS

PASS/FAIL CRITERIA:

No Part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge of the sample. If any part of any hole or any part of the lowest boundary of any flame, reaches the top edge or either vertical edge, or if there is any separation of any flaming debris droplets in the testing of one specimen, a further six specimens must be tested and comply with the above requirements, the fabric shall be deemed to conform to the requirements of type B of BS 5867-2

CONCLUSION:

The sample supplied **meets** the type B performance requirement of BS 5867-2: 2008 when tested in accordance with BS EN ISO 15025: 2002 Procedure A (Surface Ignition) before and after cleansing.

END OF REPORT