



Date of Issue: 7/28/2023 Report Number: 23-002230

Revision Number:1

Date Order Received: 07/17/2023

For the Account of: Camira Fabrics Ltd.

Meltham Mills Meltham

Holmfirth. West Yorkshire HD9 4AY

United Kingdom

Client's Identification: ReSKU 2.0

## **CERTIFICATE OF TESTING**

**TEST PERFORMED:** NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2013; Fabric Cover Test and UFAC Fabric Classification Test Method – 1990; Standard Test Methods for Cigarette Ignition Resistance of Components of Upholstered Furniture ASTM E 1353-16 – Cover Fabric Test

## **TEST RESULTS**

| Specimen | Char Length (in |
|----------|-----------------|
| 1        | 0.5             |
| 2        | 0.4             |
| 3        | 0.5             |

**NOTES** 

**Test Conditions:** 70 ±4°F, 65 ±5% Relative Humidity

## **ACCEPTANCE CRITERIA**

- 1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 45 mm (1.75 in; ASTM states 1.8 in.) or less, the fabric is classified a Class I cover fabric.
- 2. If the vertical char of the test specimen greater than 45 mm (1.75 in.; ASTM states 1.8 in), the fabric is classified a Class II cover fabric.
- 3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a Class II cover fabric.

| CONCLUSION | Based on the above Results and Acceptance Criteria, the item tested is: |
|------------|---|
|            | ⊠ Class I   |
|            | ☐ Class II  |

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature Date Order Completed: 07/28/2023