

Our Ref: SW/SW

8 November 2024

Report 428316
Page: 1 of 3

 Camira Fabrics Limited
 Meltham Mills
 Meltham
 United Kingdom
 West Yorkshire
 HD9 4AY

Contact: Luke Russell;Amanda Jack

DATE RECEIVED	:	30 OCT 2024
QUALITY/REFERENCE	:	OCEANIC + ECO FR
REPUTED FIBRE CONTENT	:	NOT GIVEN
FABRIC DESCRIPTION	:	WOVEN
COLOUR/DESIGN	:	ABYSS
STYLE NUMBER	:	555238
ORDER NUMBER	:	83A29921
PERFORMANCE STANDARD	:	GENERAL
TEST PERFORMANCE DATE(S)	:	30/10/2024 - 08/11/2024


REPORT SUMMARY

Tests	Method	Pass	Fail	Requirement
Resistance to abrasion	BS EN ISO 12947-2:2016 Abrasion			No requirement

Eurofins MTS Consumer Product Testing UK Ltd
 118 Lupton Avenue, Leeds, West Yorkshire, LS9 6ED
 Tel: 0113 248 8830 Email: info@hstts.co.uk
 Registered No. 7337435 VAT No. 887127683

8 November 2024

Report 428316**Page: 2 of 3****S. WISEMAN**
LABORATORY DIRECTOR

This report may not be reproduced except in full without the written approval of Eurofins MTS Consumer Product Testing Services Limited. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.

8 November 2024

Report 428316**Page: 3 of 3****PHYSICAL****BS EN ISO 12947-2:2016 Abrasion**

12 kPa load.

Number of rubs to breakdown:
Head 1 100,000+
Head 2 100,000+
Head 3 100,000+
Head 4 100,000+

Requirement:

No requirement