

Nepshaw Lane South, Morley, Leeds, LS27 7JQ Materials Testing Manager: D. J. Brockbank t: 0113 393 9791 e: dbrockbank@wyjs.org.uk www.wyjs.org.uk/materialstesting



TEST REPORT

Client:	Camira Fabrics Ltd Meltham Mills Meltham West Yorkshire HD9 4AY
Entry No:	70114
Date received:	11/05/2015
Client's Description:	Sample of fabric: D7408A Mustard (Cedar unbacked) Gravity, Call 3266
Test Required:	Flammability BS 7176 Low Hazard
Pre-treatment:	None
Conditioning:	A minimum of 24 hours at 50+/-5% Relative Humidity, 23+/-2° C
Date Tests Completed:	14/05/2015
Method of Test:	BS EN 1021-1: 2006 – smouldering cigarette BS EN 1021-2: 2006 – match flame equivalent

Ignition Source	Observations	Result
Smouldering	No flaming or progressive smouldering was observed within one hour of	PASS
cigarette	placement of the cigarettes.	
Match flame	Flaming ceased within the specified two minute period after removal of the	PASS
equivalent	butane flame and no progressive smouldering occurred.	

Note: A 35 kg/m³ CMHR foam (Carpenters RX36-125) which meets the requirements of Annex A of BS 7176 was used as the filling

The above tests relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Comments

BS 7176: 2007 + A1: 2011 relates to labelling of furniture. If an item of furniture was manufactured from a composite of the fabric and foam tested above then it would comply with the low hazard category flammability requirements provided that it was tested every 2.500 units or once per month as required by Para 5 of BS 7176.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein

Dale Brockbank Materials Testing Manager 31 May 2015

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.

Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.

Uncertainty budgets for test methods contained within this report are available on request. This Cartificate relates only to the sample required and upleas that sample has been drawn b

This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



