
FLAMMABILITY TEST CERTIFICATE – 80624

COMPANY DETAILS: CAMIRA FABRICS LTD
MELTHAM MILLS, MELTHAM
WEST YORSHIRE, HD9 4AY

CONTACT NAME(S): REBECCA GRIMES
TEL: 01924 481 366
EMAIL: rebecca.grimes@camirafabrics.com

DATE RECEIVED: 17/02/2020
DATE TESTED: 21/02/2020
DATE ISSUED: 21/02/2020
PO NUMBER: 7730

SAMPLE DESCRIPTION: GRAVITY
COLOUR: LAVENDER
QUALITY/BATCH REF: BATCH: 377801
MODEL REF: HCPC02
COMPOSITION: NOT STATED
SAMPLE END USE: NOT STATED
MANUFACTURER: NOT STATED
SUPPLIER/BUYER: NOT STATED

SPECIFICATION/REQUIRMENT:

BS 7176:2007+A1:2011 – Specification for the resistance to ignition of upholstered furniture for non-domestic seating by testing composites. (Low Hazard)

TEST METHOD:

BS EN 1021-1:2006 – Furniture – Assessment of the ignitibility of upholstered furniture. Ignition source smouldering cigarette.

BS EN 1021-2:2006 – Furniture – Assessment of the ignitibility of upholstered furniture. Ignition source match flame equivalent.

PRE-TREATMENT:

Water Soak procedure in accordance with Annex D of BS EN 1021-1:2006.

CONDITIONING:

The sample was conditioned for 72 hrs in ambient conditions for at least 24 hrs in a specified atmosphere at $23 \pm 2^{\circ}\text{C}$ and $50 \pm 5\%$ r h.

Authorised By:



Zeb Alam
Operations Director

Mark Jones
Quality Manager

Karen Brooks
Managing Director

FLAMMABILITY TEST CERTIFICATE – 80624

TEST RESULTS:

“The Following test results relate only to the ignitibility of the combination of the materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.”

| TEST CRITERIA – 1021-1 (CIGARETTE TEST) | INITIAL TEST | REPEAT TEST |
|---|--|--|
| FILLING MATERIAL USED: | CMHR 35 | CMHR 35 |
| Cigarette ceased smouldering within (Min(s)) | <60.00 | <60.00 |
| PROGRESSIVE SMOULDERING CRITERIA (3.1) | | |
| Unsafe escalating combustion (3.1a) | NO | NO |
| Smoulders to extremities (3.1b) | NO | NO |
| Smoulders through thickness (3.1c) | NO | NO |
| Smoulders for more than 1 hr (3.1d) | NO | NO |
| Presence of active smouldering on final examination? (3.1e) | NO | NO |
| Evidence of melting, charring, dripping? | Melting: <input checked="" type="checkbox"/> | Charring: <input checked="" type="checkbox"/> Dripping: <input type="checkbox"/> |
| FLAMING CRITERIA (3.2) | | |
| Cover Split? | YES | YES |
| Occurrence of flames? | NO | NO |
| TEST RESULT | PASS | PASS |

| TEST CRITERIA – 1021-2 (MATCH TEST) | 1 st Test | 2 nd Test | 3 rd Test |
|--|--|--|----------------------|
| FILLING MATERIAL USED: | CMHR 35 | CMHR 35 | CMHR 35 |
| Flaming Ceased: Min(s) Sec(s) | 0.05 | 0.00 | 0.00 |
| PROGRESSIVE SMOULDERING CRITERIA (3.1) | | | |
| Unsafe escalating combustion (3.1a) | NO | NO | NO |
| Smoulders to extremities (3.1b) | NO | NO | NO |
| Smoulders through thickness (3.1c) | NO | NO | NO |
| Smoulders for more than 1 hr (3.1d) | NO | NO | NO |
| Evidence of melting, charring, dripping? | Melting: <input checked="" type="checkbox"/> | Charring: <input checked="" type="checkbox"/> Dripping: <input type="checkbox"/> | |
| FLAMING CRITERIA (3.2) | | | |
| Unsafe escalating combustion (3.2a) | NO | NO | NO |
| Test assembly consumed (3.2b) | NO | NO | NO |
| Flaming to extremities and thickness (3.2c) (3.2d) | NO | NO | NO |
| Flaming continued for more than 120 seconds | NO | NO | NO |
| Cover split? | NO | NO | NO |
| TEST RESULT | PASS | PASS | PASS |

CONCLUSION:

The sample supplied **meets** the test criteria of BS 7176:2007 + A1:2011 (Low Hazard)

END OF REPORT