

For the Account of

Camira Fabrics Ltd.
Meltham Mills
Meltham
Holmfirth, West Yorkshire HD9 4AY
United Kingdom

Client's Identification

Nesta

CERTIFICATE OF TESTING

TEST PERFORMED Standard Test Method for Abrasion Resistance of Textile Fabrics (Oscillatory Cylinder Method) ASTM D 4157-13(2022)

TEST RESULTS

	Number of Double Rubs	Warp (Length) Specimens	Fill (Width) Specimens
Specimen #1	100,000	Moderate wear	Moderate wear
Specimen #2	100,000	Moderate wear	Moderate wear

INTERPRETATION USED

- ☐ Option 1 The end point is reached on a woven fabric when two or more yarns have broken or on a knitted fabric, when a hole appears.
- ☒ Option 2 The end point is reached when there is a change in shade or appearance that is sufficient to cause a customer to complain.

NOTES

Test Conditions 70 ±4°F, 65 ±5% Relative Humidity
Sampling As Received
Abradant Used ☒ ACT Standard #10 Cotton Duck ☐ Wire Screen
Samples Backed with
Masking Tape ☒ Yes ☐ No
Tension 4 pounds
Compression 3 pounds

ACCEPTANCE CRITERIA

ACT Performance Guideline Criteria

Woven + Knitted	Low Traffic / Private Spaces	High Traffic / Public Spaces
Upholstery Indoor / Outdoor	15,000 cycles, minimum	30,000 cycles, minimum
Coated Fabrics	Low Traffic / Private Spaces	High Traffic / Public Spaces
Upholstery Indoor / Outdoor	n/a	50,000 cycles, minimum

CONCLUSION

Based on the above Results and the ACT Performance Guideline, the item tested meets the requirements for:

- ☐ Unrated
☐ Low Traffic / Private Spaces
☒ High Traffic / Public Spaces

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



Authorized Signature

Date Order Completed: 12/12/2025