

Our Ref: SW/SW

25 March 2025

Report 431061/2
Page: 1 of 3

Camira Transport Fabrics Limited
Meltham Mills
Meltham
West Yorkshire
UK
HD9 4AY

Contact: Luke Russell

DATE RECEIVED : 27 FEB 2025
QUALITY/REFERENCE : REPLAY ZERO + ECO FR
REPUTED FIBRE CONTENT : NOT GIVEN
FABRIC DESCRIPTION : WOVEN
COLOUR/DESIGN : WORKOUT
STYLE NUMBER : 561228
ORDER NUMBER : 81A31625

PERFORMANCE STANDARD : GENERAL

TEST PERFORMANCE DATE(S) : 28/03/2025


REPORT SUMMARY

Tests	Method	Pass	Fail	Requirement
Resistance to abrasion	BS EN ISO 12947-2:2016 Abrasion			No requirement

Eurofins MTS Consumer Product Testing UK Ltd
118 Lupton Avenue, Leeds, West Yorkshire, LS9 6ED
Tel: 0113 248 8830 Email: info@hstts.co.uk
Registered No. 7337435 VAT No. 887127683

25 March 2025

Report 431061/2**Page: 2 of 3****S. WISEMAN
LABORATORY DIRECTOR**

This report may not be reproduced except in full without the written approval of Eurofins MTS Consumer Product Testing Services Limited. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.

Eurofins MTS Consumer Product Testing UK Ltd
118 Lupton Avenue, Leeds, West Yorkshire, LS9 6ED
Tel: 0113 248 8830 Email: info@hstts.co.uk
Registered No. 7337435 VAT No. 887127683

25 March 2025

Report 431061/2**Page: 3 of 3****PHYSICAL****BS EN ISO 12947-2:2016 Abrasion**

12 kPa load.

Requirement:

No requirement

Number of rubs to breakdown:
Head 1 100,000+
Head 2 100,000+
Head 3 100,000+
Head 4 100,000+
Shade change after 3,000 rubs: Grade 4-5
Shade change after 5,000 rubs: Grade 4-5