



Date of Issue: 1/10/2024 Report Number: 23-003659

Revision Number:1

Date Order Received: 12/04/2023

For the Account of: Camira Fabrics Ltd.

Meltham Mills Meltham

Holmfirth, West Yorkshire HD9 4AY

United Kingdom

Client's Identification: ReSKU 2.0 plus FR treatment G

FR Treatment G

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2019 – Test #1

TEST RESULTS

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	45.4	40.5	11	0.0	0.0
2	44.4	40.0	10	0.0	0.0
3	44.3	40.0	10	0.0	0.0
4	45.7	41.2	10	0.0	0.0
5	46.3	42.2	9	0.0	0.0
6	44.9	40.8	9	0.0	0.0
7	44.4	40.7	8	0.0	0.0
8	43.9	40.3	8	0.0	0.0
9	45.3	39.2	13	0.0	0.0
10	46.0	37.8	18	0.0	0.0
Average	45.1	40.3	11	0.0	0.0

approximate weight (oz./sq. yd): 22.2		./sq. yd): 22.2	Standard Deviation: 3.0	Average + 3 SD: 20.0		
roduct	Configuration:	⊠ Single Layer	☐ Multi Layer			
			or minimum 30 minutes apery	☐ 70 ±2°F & 65 ±2%RH for minimum 24 hours		
CCEPT	ANCE CRITERI	A				
fterflam	e is required to	be recorded; however, it is not	factored into the Acceptance Crite.	ria		
1. 2.	seconds per s	pecimen for the sample of 10 s	pecimens, the material shall be rec	per continue to burn for more than an average of 2 corded as failing. (Flaming Drip) 40 percent, the material shall be recorded as failing.		
3.				40 percent, the material shall be recorded as failing.		
3. 4.						
٦.		s passing this test and shall be		of the conditions indicated above, the material shall		
ONCLU	ISION Base	ed on the above Results and A	cceptance Criteria, the item tested:			
	⊠ (Complies				
		oes Not Comply				
	CATION I certify by the standard		tained after testing specimen in ac	cordance with the procedures and equipment		
Bert	ia Stiver					
uthorize	d Signature			Date Order Completed: 12/05/2023		

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-lab.com

Page 1 of 1