



Confidential Report

Our Ref: 27/05255A/01/20



1066

Notified Body
for PPE Directive,
Construction Products Regulation
& Marine Equipment Directive
I.D. No. 0338 & 0339



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 28 February 2020
Our Ref: 27/05255A/01/20
Your Ref:
Page: 1 of 5

Client: Camira Fabrics Limited
The Watermill
Wheatley Park
Mirfield
West Yorkshire
WF14 8HE

Job Title: Fire Test on One Sample of Fabric

Client's Order No: 83A07282 (C71974)

Date of Receipt: 17 January 2020

Description of Sample(s): One sample of fabric:
Ref: Lucia I2
Batch No: 436294
Colour: D9078M

Work Requested: We were asked to make the following test(s):
BS 476 Part 7

Note: This report relates only to the samples submitted and as described in the report.

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Limited
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 28 February 2020

Our Ref: 27/05255A/01/20
Your Ref:

Page: 2 of 5

Client: Camira Fabrics Limited

FIRE TESTS ACCORDING TO BS 476-7:1987

Fire tests on building materials and structures. Method of test to determine the classification of the surface spread of flame of products

Date of Test: 26/02/2020

Conditioning

The sample was conditioned to constant mass at a temperature of $23\pm 2^{\circ}\text{C}$ and a relative humidity of $50\pm 10\%$.

Procedure

The test was carried out in accordance with BS 476-7:1987. The composite sample was supplied by the sponsor of the test. The sample was tested as adhered to a 12mm thick calcium silicate board, using PVA adhesive.

The following were recorded:-

- a) the time at which the flame front crosses each vertical reference line;
- b) the maximum extent of flame spread during the first 1.5 min from the start of the test;
- c) the maximum extent of flame spread during the whole test i.e. 10 min or less (if applicable)
- d) the time (and distance) at which maximum flame spread is reached.

The flame spread at 1.5min and the final flame spread results were compared with the standard class limits and a classification was assigned.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Limited
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved

Client: Camira Fabrics Limited

Requirements

The class limits for flamespread, detailed in BS 476:Part 7: are set out below.

| | Flame spread at 1.5 min (mm) | Final flame spread (mm) |
|---------|------------------------------|-------------------------|
| Class 1 | 165 (+25) | 165 (+25) |
| Class 2 | 215 (+25) | 455 (+45) |
| Class 3 | 265 (+25) | 710 (+75) |
| Class 4 | Exceeding Class 3 limits. | |

A definitive classification is based on a sample of six specimens and the figure in brackets gives the tolerance by which only one specimen in six may exceed the class limit assigned.

Results

The test results relate only to the behaviour of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

| Time for flame spread to reach (s) (mm) | | | | | | | | Flame spread at 1.5 min (mm) | Maximum flame spread (mm) | Time to reach maximum flame spread (s) |
|---|-----|-----|-----|-----|-----|-----|-----|------------------------------|---------------------------|--|
| 75 | 165 | 215 | 265 | 455 | 710 | 785 | 825 | | | |
| -- | -- | -- | -- | -- | -- | -- | -- | 50 | 50 | 60 |
| -- | -- | -- | -- | -- | -- | -- | -- | 50 | 50 | 60 |
| -- | -- | -- | -- | -- | -- | -- | -- | 50 | 50 | 60 |
| -- | -- | -- | -- | -- | -- | -- | -- | 50 | 50 | 60 |
| -- | -- | -- | -- | -- | -- | -- | -- | 50 | 50 | 60 |
| -- | -- | -- | -- | -- | -- | -- | -- | 50 | 50 | 61 |



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk


Date: 28 February 2020
Our Ref: 27/05255A/01/20
Your Ref:
Page: 4 of 5


Client: **Camira Fabrics Limited**

Classification

The results indicate the composite sample meets the performance requirements of Class 1.

Uncertainty of measurement has not been taken into account when presenting the test result. The relevant uncertainty value is included as an annex which forms an integral part of the report.

Reported by:.....  A Shute, Senior Lab Technician

Countersigned by:.....  P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Limited
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 28 February 2020

Our Ref: 27/05255A/01/20
Your Ref:

Page: 5 of 5


Client: Camira Fabrics Limited

Uncertainty Budget - Annex

The overall uncertainty budget for BS 476-7:1987 is as follows:-

BS 476-7:1987

Overall: $\pm 20\%$



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Limited
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved