



# Confidential Report

Our Ref: 27/06424/03/24





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 12 April 2024

Our Ref: 27/06424/03/24  
Your Ref: 83A26588

Page: 1 of 5

**Client:** Camira Fabrics Ltd

The Watermill  
Wheatley Park  
Mirfield  
West Yorkshire  
WF14 8HE

**Job Title:** Fire test on one sample of Fabric

**Clients Order Ref:** 83A26588

**Date of Receipt:** 21 March 2024

**Description of Sample:** One sample of fabric, referenced; Main Line Flax/Main Line Twist/Monochrome Sett, Batch: 532166, Colour: Ply.

**Work Requested:** We were asked to make the following test(s):

BS 476 Part 7

- \* subcontracted test, UKAS accredited
- \*\* subcontracted test, EN ISO/IEC 17025 accredited
- \*\*\* not UKAS accredited



1066

Note: This report relates only to the items tested.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 12 April 2024

Our Ref: 27/06424/03/24  
Your Ref: 83A26588

Page: 2 of 5

Client: Camira Fabrics Ltd

## FIRE TESTS ACCORDING TO BS 476-7:1997

**Fire tests on building materials and structures. Method of test to determine the classification of the surface spread of flame of products.**

Date of Test: 11/04/2024

### Conditioning

The sample was conditioned to constant mass at a temperature of  $23\pm 2^{\circ}\text{C}$  and a relative humidity of  $50\pm 10\%$  and maintained in this condition until required for testing.

### Mounting Method

Each specimen was tested fully adhered to a 12mm calcium silicate board, using PVA adhesive.

### Procedure

The test was carried out in accordance with BS 476-7:1997.

The following were recorded: -

- the time at which the flame front crosses each vertical reference line;
- the maximum extent of flame spread during the first 1.5 min from the start of the test;
- the maximum extent of flame spread during the whole test i.e. 10 min or less (if applicable)
- the time (and distance) at which maximum flame spread is reached.

The flame spread at 1.5min and the final flame spread results were compared with the standard class limits and a classification was assigned.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
 Telephone: +44 (0) 113 259 1999  
 Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
 Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 12 April 2024

Our Ref: 27/06424/03/24  
 Your Ref: 83A26588

Page: 3 of 5

**Client:** Camira Fabrics Ltd

## Requirements

The class limits for flamespread, detailed in BS 476: Part 7: are set out below.

	Flame spread at 1.5 min (mm)	Final flame spread (mm)
Class 1	165 (+25)	165 (+25)
Class 2	215 (+25)	455 (+45)
Class 3	265 (+25)	710 (+75)
Class 4	Exceeding Class 3 limits.	

A definitive classification is based on a sample of six specimens and the figure in brackets gives the tolerance by which only one specimen in six may exceed the class limit assigned.

## Results

The test results relate only to the behaviour of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Time for flame spread to reach (s)								Flame spread at 1.5 min (mm)	Maximum flame spread (mm)	Time to reach maximum flame spread (s)
75	165	215	265	455	710	785	825			
--	--	--	--	--	--	--	--	65	65	60
--	--	--	--	--	--	--	--	60	60	60
--	--	--	--	--	--	--	--	70	70	60
--	--	--	--	--	--	--	--	70	70	60
--	--	--	--	--	--	--	--	65	65	60
--	--	--	--	--	--	--	--	60	60	60





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 12 April 2024

Our Ref: 27/06424/03/24  
Your Ref: 83A26588

Page: 4 of 5

**Client:** Camira Fabrics Ltd

### Classification

The results indicate the sample meets the performance requirements of Class 1.

### Note

Test BS 476-7:1997 is accredited under our flexible scope policy.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (<https://www.bttg.co.uk/about-us/decision-rules-policy/>) for further information.

Reported by:  ..... G Harvey (Mr), Laboratory Technician

Countersigned by:  ..... A Shute, Section Leader

Enquiries concerning this report should be addressed to Customer Services.



Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 12 April 2024

Our Ref: 27/06424/03/24  
Your Ref: 83A26588

Page: 5 of 5

**Client:** Camira Fabrics Ltd

## Uncertainty Budget

The overall uncertainty budget for BS 476-7:1997 is as follows:-

Overall:  $\pm 12\%$



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.