

Textiles and Apparel Solutions Centre, The Warehouse, Brewery Lane, Leigh, Lancashire, WN7 2RJ, UK Telephone: +44 (0) 1942 265700

Facsimile: +44 (0) 1942 670 788 www.intertek.com/consumergoods

## **BS EN 14465:2003 Test Report**

Report Ref:	LEHTX00821037A	Buying Division: NONE GIVEN	
Date Received:	17/06/2015	Date Issued: 22/06/2015	

Company Name & Address	CAMIRA FABRICS LIMITED  MELTHAM MILLS  MELTHAM  WEST YORKSHIRE
	HD9 4AY
Contact Name	AMANDA HEELEY/

Order No.:	52495
Description:	CEDAR LAVENDER
Colour(s):	CEDAR LAVENDER
Supplier:	NONE GIVEN
End Use:	NONE GIVEN
Quoted Composition:	NONE GIVEN
Ref/Style/Stroke No.:	NONE GIVEN
Quality:	NONE GIVEN
Batch No.:	NONE GIVEN
Spec. No.:	TABLE 1

Test	Method	Colour	Pass/Fail
ABRASION RESISTANCE (FLAT WOVEN)	BS EN ISO 12947-2/BS EN 14465: 2003 ANNEX A		Pass A

Jess Lucas (Technician)

Aucas

Lab Report:LEHTX00821037A: Page 1 of 3







Textiles and Apparel Solutions Centre, The Warehouse, Brewery Lane, Leigh, Lancashire, WN7 2RJ, UK Telephone: +44 (0) 1942 265700

Facsimile: +44 (0) 1942 670 788 www.intertek.com/consumergoods

Upholstery - Martindale Abrasion (12 kPa Load) RH 65% +/-4% / T						
Sample		Results			Minimum Requirements	
					A=35,000 B=12,000-30,000	
Fabric Type	H	Heads 2,3 & 4 No fabric breakdown @ 65,000 revs				
Flat Woven		Fabric breakdown @ 70,000 revs				
	Please not	Please note: The martindale abrasion was taken to end point @ the customers request.				
Overall Result		66,000 revs				
Overall Performance L						
	BS 2543	2004 Classification (M	nimum levels for custo	omer reference)		
	LD	GD	HD	GC	sc	
Flat Woven	B - 15,000	B - 20,000	B - 25,000	B - 30,000	A - 40,000	
Figured Weaves	B - 12,000	B - 15,000	B - 20,000	B - 30,000	A - 40,000	
Woven/Flocked/Non- Woven Pile Fabrics	C - 15,000	C - 20,000	B - 25,000	B - 25,000	B - 30,000	
Knitted	B - 15,000	B - 20,000	B - 25,000	B - 25,000	B - 30,000	

Lab Report:LEHTX00821037A: Page 2 of 3







Textiles and Apparel Solutions Centre, The Warehouse, Brewery Lane, Leigh, Lancashire, WN7 2RJ, UK Telephone: +44 (0) 1942 265700

Facsimile: +44 (0) 1942 670 788 www.intertek.com/consumergoods

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

Lab Report:LEHTX00821037A: Page 3 of 3



