

Our Ref: SW/BR 18 September 2020

<u>Page 1 of 3</u>

Camira Fabrics Limited Meltham Mills Meltham Huddersfield West Yorkshire HD9 4AY

Contact: Luke Russell

DATE RECEIVED : 16 SEP 2020
QUALITY/REFERENCE : TARGET
REPUTED FIBRE CONTENT : NOT GIVEN
FABRIC DESCRIPTION : WOVEN
COLOUR/DESIGN : SCUBA
STYLE NUMBER : 459757
END USE : LIBROUS STEEL

END USE : UPHOLSTERY ORDER NUMBER : 83A09060

PERFORMANCE STANDARD : NOT SPECIFIED



### REPORT SUMMARY

Tests	Method	Pass	Fail	Requirement
Colour fastness to dry cleaning	BS EN ISO 105-D01:2010			No requirement
Chlorinated water	BS EN ISO 105-E03:2010			No requirement
	Chlorinated Water			





18 September 2020

<u>Page 2 of 3</u>

S. WISEMAN LABORATORY DIRECTOR

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.





18 September 2020

# <u>Page 3 of 3</u>

### **COLOUR FASTNESS TO:**

## BS EN ISO 105-D01:2010 Dry Clean

Using 99% Methylated spirit

 S/C	Ate.	Cot.	Nyl.	Pol.	Acr.	Wool	Requirement:
4-5	4-5	4-5	4-5	4-5	4-5	4-5	No requirement

#### BS EN ISO 105-E03:2010 Chlorinated Water

1.3% solution

 Shade change	Requirement:
4-5	No requirement

